

PTFE & FEP BURST PRESSURE TEST												
SIZE (mm.)			BURST PRESSURE (Bar)									
			50 °C		75 °C		100 °C		150 °C		200 °C	
ID	OD	Thickness	PTFE	FEP	PTFE	FEP	PTFE	FEP	PTFE	FEP	PTFE	FEP
2.00	4.00	1.00	100.00	120.00	83.00	85.00	67.00	60.00	46.00	40.00	35.00	20.00
4.00	6.00	1.00	53.50	60.00	41.50	42.50	33.50	30.00	23.00	20.00	17.50	10.00
6.00	8.00	1.00	35.67	40.00	27.67	28.33	22.33	20.00	15.33	13.33	11.67	6.67
8.00	10.00	1.00	26.75	30.00	20.75	21.25	16.75	15.00	11.50	10.00	8.75	5.00
10.00	12.00	1.00	21.40	24.00	16.60	17.00	13.40	12.00	9.20	8.00	7.00	4.00
12.00	14.00	1.00	17.83	20.00	13.83	14.17	11.17	10.00	7.67	6.67	5.83	3.33
14.00	16.00	1.00	15.29	17.14	11.86	12.14	9.57	8.57	6.57	5.71	5.00	2.86
16.00	18.00	1.00	13.38	15.00	10.38	10.63	8.38	7.50	5.75	5.00	4.38	2.50
18.00	20.00	1.00	11.89	13.33	9.22	9.44	7.44	6.67	5.11	4.44	3.89	2.22
3.18	6.35	1.59	106.66	119.62	82.74	84.73	66.79	59.81	45.86	39.87	34.89	19.94
6.35	9.53	1.59	53.58	60.09	41.57	42.57	33.55	30.05	23.04	20.03	17.53	10.02
9.53	12.70	1.59	36.59	39.92	27.61	28.27	22.29	19.96	15.30	13.31	11.64	6.65
12.70	15.88	1.59	26.79	30.05	20.78	21.28	16.78	15.02	11.52	10.02	8.76	5.01
15.88	19.05	1.59	21.36	23.95	16.57	16.97	13.37	11.98	9.18	7.98	6.99	3.99
19.05	22.23	1.59	17.86	20.03	13.86	14.19	11.18	10.02	7.68	6.68	5.84	3.34
22.23	25.40	1.59	15.26	17.11	11.84	12.12	9.55	8.56	6.56	5.70	4.99	2.85

+GF+ SIGNET
GEORGE FISCHER +GF+ Piping Systems

GRUNDFOS
ALLDOS

SIMONA *topflo*

E.L.B.
FÜLLSTANDSGERÄTE

SANKING

Dosing and Piping Technology

DOSELINE CO.,LTD

588/77 Hathairat Rd., Bangchan, Klongsamwa, Bangkok 10510

Tel. : (+66)2130-2170 Fax. : (+66)2130-2236 E-Mail : doselinethai@hotmail.com ; www.doseline.com

DoseLine